

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶ : G03F 1/00	A1	(11) International Publication Number: WO 98/16874 (43) International Publication Date: 23 April 1998 (23.04.98)
(21) International Application Number: PCT/IL97/00330 (22) International Filing Date: 14 October 1997 (14.10.97) (30) Priority Data: 08/733,103 16 October 1996 (16.10.96) US (71) Applicant (for all designated States except US): J.G. SYSTEMS INC. [IL/IL]; P.O. Box 58155, 61581 Tel Aviv (IL). (71)(72) Applicant and Inventor: GRUNWALD, John, J. [IL/IL]; Hameshorer Street 4, 52650 Ramat Aviv (IL). (74) Agent: COHEN, A., David; P.O. Box 60, 84100 Beer Sheva (IL).		(81) Designated States: AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GE, GH, HU, ID, IL, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZW, ARIPO patent (GH, KE, LS, MW, SD, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, ML, MR, NE, SN, TD, TG). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: PROCESS FOR IMAGING A FLEXO-GRAPHIC PRINTING PLATE FROM LIQUID PHOTOPOLYMERS AND WITHOUT USING PHOTOTOOLS (57) Abstract In the process of making a flexographic printing plate, the liquid photopolymerizable composition is cast against an IR laser-imageable element which then acts as an <i>in situ</i> negative for subsequent UV flood exposure.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav	TM	Turkmenistan
BF	Burkina Faso	GR	Greece		Republic of Macedonia	TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's	NZ	New Zealand		
CM	Cameroon		Republic of Korea	PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

PROCESS FOR IMAGING A FLEXO-GRAPHIC PRINTING PLATE FROM LIQUID PHOTOPOLYMERS AND WITHOUT USING PHOTOTOOLS

1. Field of the Invention

The printing industry in general, and the relief printing (flexography) business in particular, are constantly striving to reduce cycle time, and achieve rapid globalization of the information to be printed. This means standardizations, affording to print a given pattern (texts, graphics, etc.) uniformly at any geographical location, worldwide, even for relatively short runs. Such demands of reduced cycle time are best achieved by going directly from a digital file of the pattern to be printed to a final plate, by skipping the huge numbers of steps involved between the pattern/graphics to be printed, and the final plate. The technique commonly used to achieve such short cycle times is known as "Direct-to-Plate".

In the offset arena, companies such as Presstek, Indigo, Xerox, 3M, and others, are offering systems that are successfully addressing above requirements. In the flexography business, DuPont and others are beginning to introduce a Direct-to-Plate, solid sheet, flexographic process, known as "CYREL™ Digital Direct Imaging SYSTEM". (CDDI).

No Direct-to-Plated processes are known in the prior art that use liquid photopolymeric compositions. This invention addresses the issue of "Direct-to-Plate" via liquids (DPVL) wherein phototools can be eliminated. A very desirable need.

Indeed, while solid sheet flexographic printing plates are easier to use, and therefore, currently predominate, liquid photo-polymeric products have numerous advantages over solids:

1. Environmentally friendly. Easier to recycle than solid sheet compositions.
2. More economical than solid photo-polymeric compositions when compared on a cost per square feet basis.
3. When applied according to best-practice, printing quality can be superior than with solid sheets.

The technical problem in achieving direct-to-plate capability with liquid photopolymeric compositions, resides in the difficulty to deposit a layer of a stable, laser ablatable coating, on a liquid surface, because of the very dynamic nature of liquid, i.e.: their fluidity that causes intermixing of adjoining layers.

2. Description of the Prior Art

U.S. Patent 4,137,081, 4,442,302, the disclosures of which are incorporated herein by reference in their entirety, describe liquid photopolymers that are actinically imagewise exposed using phototools. Many of the basic teachings in the foregoing patents, concerning the typical use of liquid photopolymers in printing, are applicable to the practice of this invention. U.S. Patent 5,262,275, the disclosure of which is incorporated herein by reference in its entirety, describes solid sheet, UV photosensitive compositions, wherein the top layer is laser ablatable, using computer-guided mechanisms. The laser ablated areas are transparent to UV radiation, whereas unablated areas are opaque to UV. Following laser scanning to obtain the desired pattern, the solid sheet is "flood-exposed" using UV lamps, as is well known in the art. This is followed by development, to achieve the desired printing pattern.

Liquid systems of flexographic plates are well entrenched in the industry, and supplied by companies such as MacDermid, W.R. Grace, Asahi and others, but, unlike with solid sheet flexographic plates, no known techniques are available to make them adaptable for use without phototools (i.e. via *in-situ* negatives or direct ablation of the desired relief image). This objective is addressed by one of the methods described further.

3. Objectives of the Invention

It is an objective of the present invention to prepare flexographic printing plates that do not require use of phototools or negatives wherein plates are made of liquid photopolymeric compositions as opposed to solid sheets. Further objectives will become known from reading the specifications.

4. Summary of the Invention

The present invention relates to an improved process for manufacturing flexographic printing plates that do not require the use of phototools of the prior art, comprising.

1. Casting a liquid photopolymeric composition against an IR laser-ablatable imaging element, which element comprises at least one IR laser-ablatable, UV opaque layer sandwiched between two polymeric films, one of which is transparent to actinic radiation.
2. Imagewise scanning the IR-ablatable layer with an IR laser.
3. Flood-exposing the liquid photopolymer layer to actinic radiation.
4. Peeling away the IR imaging element to expose the UV flood-exposed photopolymer.
5. Washing away the actinically unexposed liquid photopolymer areas in a suitable developer to obtain the desired relief printing plate, as needed.

5. Brief Description of the Drawings

Figure 1 illustrates an IR laser-abatable layer sandwiched between a non-adherent peelable polyester layer and a UV-transparent support film.

Figure 2 depicts an IR laser abatable layer sandwiched between a polymeric film transparent to IR laser and a UV-transparent support film.

6. Detailed Disclosure of the Invention

The present invention can be carried out according to two general methods:

Method No. 1

The liquid photosensitive layer (usually consisting of a binder, a monomer and negative-acting UV radical polymerization initiator) is cast against a "sandwich" composite (element), instead of a negative or phototool as currently practiced in the art. The construction of the sandwich film is given in Figure 1.

The IR-abatable layer can be vacuum-metallized T, Cu, Al, W, other metals or metal oxides (i.e.: TiO_2 , Cu_2O , etc) or carbon lack, that ablated at reasonably low energies and without residues.

Alternately, the IR-ablatable layer may contain a binder such as acrylic polymers and IR dyes that maximize the absorption of IR radiation and its conversion into thermal energy needed to facilitate ablation. Still, another possibility is to simply use IR ablatable dyes, without polymeric binders.

The main essential criteria for the abatable layer are:

1. Opacity in the range of about 700 nm and higher.
2. As thin as possible (preferably in the range of about a few microns to enable ablation at reasonably low energies).

Pore-free

In the process of manufacturing a flexographic plate as per present invention, the liquid photopolymer layer is cast against polyester film (3) Fig. 1), thereby replacing the phototool of the prior art, following current techniques. The peelable top layer (1) is removed and the IR-ablatable coating (2) is "computer scanned" to obtain and *in situ* negative, which is followed by UV-flood exposure, peeling away film (3) followed, if needed, by development as practiced by the prior art.

Preferably, the IR-ablated surface (*in situ* negative) is covered by a protective transparent polymeric film prior to UV exposure. This, to avoid mechanical or other damage during UV exposure.

Method No. 2

This method offers an alternate embodiment of this invention. Specifically, it envisions the formation of an *in situ* mask, without requiring removal/peeling off the upper film covering the "sandwich", as is described in Method #1. In Method #2, the cover film is transparent to the energy delivered by the IR laser without causing optical problems, and therefore, need not to be removed. Alternatively, the top film can be co-ablated with the IR layer. The "sandwich" film is shown in Figure 2.

In the process of manufacturing a flexographic plate according to Method #2, the three layer composite ("sandwich") is placed on the exposure unit, replacing the phototool as practiced in the prior art. IR laser scanning follows, achieving an *in situ* negative by generating a pattern of transparent and opaque areas, as commanded by the computer. UV flood exposure through the *in situ* negative, achieves photo-polymerization where actinic (UV) radiation is allowed to reach the liquid photopolymers through the transparent regions of the *in situ* negative.

Method #2, by necessity, envisions the use of bleachable dyes, as opposed to ablatable coatings. Indeed, due to the presence of the upper film (no peeling-off of the top film is envisioned), ablation could cause problems because volatiles cannot freely escape unless the upper film is porous enough to accommodate the escape of gaseous/volatile products ("breathing films"), in which case ablation remains an option.

Again, following IR scanning, the composite is flood-exposed to actinic (UV) radiation to achieve insolubilization of the areas not to be washed away in the developer. This is followed by peeling away of the bottom film (3) adjacent to the liquid photopolymer that supports the IR coating, allowing development of the final plate, as needed.

Thus, the objective of this invention is similar in scope to that of U.S. Patent No. 5,262,275, except that this invention is exclusively intended for liquid photopolymers. It excludes the use of solid sheet photopolymers.

The method of this invention is summarized the following steps, though modifications thereof, are practicable by those skilled in the art:

1. Apply adjacently to the liquid photopolymer at least one IR-ablatable, UV-opaque layer supported by a polymer film which is transparent to actinic radiation.
2. Scan imagewise the IR-ablatable layer with an IR laser.
3. Flood expose the liquid photopolymer to actinic radiation.
4. Peel away the film that supports the IR-ablatable layer which is adjacent to the liquid photopolymer without damaging the UV-polymerized regions.
5. Wash away the actinically unexposed liquid photopolymer areas in a suitable developer to obtain the desired relief printing plate, as needed.

CLAIMS

1. A method of manufacturing a flexographic printing element made of liquid photopolymers and imaging it directly without the use of phototools or negatives using IR laser energy, comprising:
 - a) Applying adjacently to the liquid photopolymer at least one IR-ablatable, UV-opaque layer supported by a polymer film which is transparent to actinic radiation;
 - b) Imagewise scanning the IR-ablatable layer with an IR laser;
 - c) Flood-exposing the liquid photopolymer layer to actinic radiation;
 - d) Peeling away the film that supports the IR-ablatable layer; and
 - e) Washing away the actinically unexposed liquified photopolymer areas in a suitable developer to obtain the desired relief printing plate, as needed.
2. A method in accordance with Claim 1 wherein the IR-ablatable layer is sandwiched between a top-peelable film and a UV transparent film.
3. A method in accordance with Claim 1 wherein the top-peelable film is co-ablatable with the IR-ablatable layer.
4. A method in accordance with Claim 1 wherein the top-peelable film is peeled away prior to the IR-laser scanning.
5. A method in accordance with Claim 1 wherein the IR-ablatable layer is a material that ablates without residues.
6. A method in accordance with Claim 1 wherein the IR-ablatable layer requires energies of 10 mili Joules per cm^2 or less.
7. A method in accordance with Claim 1 wherein the IR-ablatable layer requires energies of 4 mili Joules per cm^2 or less.
8. A method in accordance with Claim 1 wherein the IR-ablatable layer is formed of materials selected from the group consisting of vacuum-metalized metals, metal oxides, carbon black, acrylic polymers containing IR dyes, and IR ablatable dyes.
9. A method in accordance with Claim 8 wherein the vacuum-metalized metals are selected from the group consisting of titanium, copper, aluminum, tungsten and mixtures thereof.

10. A method in accordance with Claim 8 wherein the vacuum-metalized oxides are selected from the group consisting of TiO_2 , Cu_2O , WO_2 , and mixtures thereof.
11. A method in accordance with Claim 1 wherein the IR-ablatable layer comprises a bleachable dye.
12. A method in accordance with Claim 3 wherein the IR-ablatable layer is a bleachable dye.
13. An imaging element comprising an IR-ablatable layer sandwiched between a top-peelable film and a UV transparent film.
14. A printing element manufactured in accordance with the process of claim 1.
15. A method of manufacturing a flexo-graphic printing element directly from a liquid phase without the use of phototools or negatives, using IR laser energy, comprising:
 - (a) providing a layer of liquid photopolymerizable composition capable of being formed into a solid upon exposure to actinic radiation;
 - (b) covering said layer of said liquid photopolymerizable composition with a UV-transparent film;
 - (c) applying adjacent said UV-transparent film in contact with said layer of liquid photopolymerizable composition at least one IR-ablatable, UV-opaque layer so that said IR-ablatable, UV-opaque layer will be supported by said UV-transparent film;
 - (d) imagewise scanning said IR-ablatable layer with an IR laser to ablate portions of said IR-ablatable layer and expose portions of said layer of liquid photopolymerizable composition in said pattern;
 - (e) flood-exposing pattern-revealed portions of said layer of liquid photopolymerizable composition to actinic radiation to solidify said portions of said layer of photopolymerizable composition; and
 - (f) washing away actinically unexposed liquid photopolymer areas to obtain a desired relief printing plate.

Fig. 1





Fig. 2



INTERNATIONAL SEARCH REPORT

Inter. Appl. No.
PCT/IL 97/00330

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 G03F1/00

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 G03F B41M

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	FR 2 232 781 A (GRACE W R LTD) 3 January 1975	1-15
Y	see the whole document	1-15
Y	US 5 262 275 A (FAN ROXY N) 16 November 1993 cited in the application see the whole document	1-15
Y	EP 0 634 695 A (GRACE W R & CO) 18 January 1995 see the whole document	1
Y	US 4 247 576 A (KUTNER ABRAHAM) 27 January 1981 see the whole document	1-15
	-/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "&" document member of the same patent family

Date of the actual completion of the international search

10 February 1998

Date of mailing of the international search report

27/02/1998

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Rasschaert, A

INTERNATIONAL SEARCH REPORT

International Application No
PCT/IL 97/00330

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	WO 94 03839 A (E.I. DU PONT DE NEMOURS AND COMPANY) 17 February 1994 see page 24, line 4 - line 6; claim 1 ---	1
A	US 5 506 086 A (VAN ZOEREN CAROL M) 9 April 1996 see the whole document -----	1

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/IL 97/00330

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
FR 2232781 A	03-01-75	AU 6984274 A BE 816067 A DE 2427788 A JP 50053106 A NL 7407727 A	11-12-75 30-09-74 02-01-75 12-05-75 10-12-74
US 5262275 A	16-11-93	CA 2140872 A DE 69308570 D DE 69308570 T DE 654150 T EP 0654150 A JP 7506201 T WO 9403838 A	17-02-94 10-04-97 17-07-97 28-09-95 24-05-95 06-07-95 17-02-94
EP 0634695 A	18-01-95	AU 665147 B AU 5945294 A BR 9402431 A CA 2121865 A CN 1111761 A DE 4339010 A JP 7017151 A NZ 260292 A	14-12-95 05-01-95 24-01-95 26-12-94 15-11-95 05-01-95 20-01-95 21-12-95
US 4247576 A	27-01-81	CA 1148040 A	14-06-83
WO 9403839 A	17-02-94	US 5607814 A CA 2140873 A EP 0654151 A JP 7509789 T	04-03-97 17-02-94 24-05-95 26-10-95
US 5506086 A	09-04-96	CA 2171770 A EP 0741329 A JP 8305007 A US 5705310 A	02-11-96 06-11-96 22-11-96 06-01-98